Impact of Nanomaterials on the Mechanical Properties of Concrete: A Comparative Study of Strength and Durability

[1]Saken Uderbayev, [2]Dr. M. Mariappan, [3]A.S. Madhusudhan Rao, [4]Mallika Jain, [5]Mr. Vishnu Kumar, [6]Aye Min Win

[1] Professor Korkyt Ata Kyzylorda University Email ID: saken.uderbayev@gmail.com Orcid ID: 0000-0003-4492-8364

[2]Associate Professor Department of Civil Engineering Dr. Mahalingam College of Engineering and Technology , Pollachi-642003, mariappan.m2009@gmail.com

[3]Department of Physics, Geethanjali College of Engineering and Technology , 501303 Hyderabad Email ID: madhuammiraju@gmail.com Orcid ID: 0009-0006-4543-4971

[4]Assistant Professor, Civil Engineering Environmental Sciences and Engineering, Bhilai Institute of Technology-Durg, Chhattisgarh Pin code: 491001 City: Durg ORCID ID: 0009-0008-2963-1339 Email : mallika.saraf@bitdurg.ac.in

[5]Assistant Professor, Mangalayatan University, Aligarh, Uttar Pradesh -202145 Department of Civil Engineering vishkum74538@gmail.com

[6]Researcher, Master of Science in Construction Management (Building Information Modelling), Faculty of Engineering and Quantity Surveying, Inti International University, 71800 Nilai Malaysia Email ID: i25034439@student.newinti.edu.my Orcid ID: 0009-0005-6104-2014

Abstract

Concrete technology through nanotechnology has been receiving a lot of interest due to the improvements in mechanical properties, durability and sustainability. However, some problems limit the enhancement of the performance of nanomaterials by integration. The purpose of this research is to mitigate these challenges through evaluating the impact of the nanomaterials, which include nano-silica, TiO_2, and carbon nanomaterials on the machine-driven and robustness characteristics of concrete containing recycled aggregates and supplementary cementitious materials. The findings of this study are useful in the enhancement of sustainable construction productivity, the minimisation of the impact on the environment, and the enhancement of structural performance. The following systematic approach was followed in this study to integrate nanomaterials in concrete mixtures and assess the effects through experimental and analytical techniques. The outcomes of the current work were further related with the compressive strength, flexural properties and micro structural improvements. The study reveals that the use of nanomaterials enhances the machine-driven properties of concrete and that nanosilica has the best potential to enhance the microstructure and reduce defects in recycled aggregate concrete. The study also reveals that more emphasis should be placed on the right amount and distribution in order to get the right results. These outcomes show the possibility of using nanomaterials in the present concrete technologies, and give a direction on how to use these nanomaterials properly and economically. The use of nanomaterials in cost effective manufacturing, their use in bulk systems and their possibilities in designing smart structures need to be researched further.

Keywords: Nanomaterials, Concrete Technology, Mechanical Properties, Durability Enhancement, Sustainable Construction

1. Introduction

New ways of enhancing the characteristics of materials employed in the edifice of structures to support the built environment are always being sought. Over the past ten years, nanomaterials have been a possibility of enhancing both mechanical characteristics and the durability and sustainability of concrete. Concrete is the most used constituent in construction across the globe and it has issues with strength, handling and the environment. The problems are as a rule solved with the help of traditional approaches that are non-efficient, and therefore new approaches including nanotechnology are used [1]. Nano materials have been receiving much attention in altering the microstructure of concrete because of their size and unique properties. Literatures have shown that the incorporation of nano silica, titanium dioxide (TiO_2) and carbon-based nanoparticles enhances compressive strength and flexural strength, other characteristics of concrete mixtures [2]. Furthermore, the incorporation of nanomaterials into the polymer matrix has been proven to improve the pore characteristics, thus improving the automatic chattels and strength of the material to peripheral stresses [3].

In construction, nanomaterials are also employed in mechanical and durability improvement, low cement content, and waste materials such as recycled aggregates. Recent research on the incorporation of nanomaterials into concrete is because of the two main benefits of enhancing the performance and diminishing the negative effects on

the environment [4]. Some of the current research has revealed that nanoparticles enhance the workability, setting time and degree of hydration of cement-based materials to be used in construction operations [5,6]. The literature review on nanomaterials in concrete is huge and the outcome is quite promising but there are still voids. The main issue is that the outcomes are rather random because of the kind of nanoparticles, their concentrations, ways of dispersion, and environmental circumstances [7]. This is because the procedures for the incorporation of nanomaterials are still undefined and hence restrict the application of these materials on a large scale [8]. The use of nanomaterials in concrete to build large edifices has to consider the economic viability and sustainability of the nanomaterials [9].

A second major issue is that some of the nanomaterials have a very large ecological footprint. The properties of concrete can be enhanced by the use of additives and the impact of manufacturing and disposal of these additives on the environment should be investigated to enhance sustainability [10]. Nonetheless, recycled aggregates and SCM containing nanomaterials are encouraging; nonetheless, the durability behaviour and the life cycle impacts of such systems are still unexplored [11]. Furthermore, the processes of how nanomaterials intercalate with cementitious matrices are not well understood. For example, it is known that the incorporation of nano-silica improves strength, but the interaction between nano-silica and hydration products at various temperatures and curing conditions is not well understood. For these reasons, these challenges have to be met to translate the laboratory research into more practical uses.

Objectives and Novelty

The primary aim of this study work therefore is to assess the impact of various nanomaterials on the power-driven characteristics and the durability of concrete. Specifically, the research aims to:

1. The impression of nano-silica, TiO_2, and carbon nanomaterials on the compressive and flexural strength of concrete is examined.
2. The effects of nanomaterials on microstructure are described in relation to pore refinement and interfacial transition zones.
3. Evaluate the environmentally friendly applications of nanomaterials for concrete with the view to using recycled aggregates and other binders.

This work is distinct from others in that it considers both performance and sustainability concerns of nanomaterial incorporated concrete. This work is not limited to mechanical improvements and contains ecological assessments to provide a comprehensive outlook of the material's capabilities [12]. However, additional advanced methods including X-ray diffraction (XRD) are employed to analyze the microstructural changes resulting from nanomaterials [13]. The purpose of this study is to examine the feasibility of using nanomaterials in recycled aggregates and supplementary cementitious materials to produce high performance green concrete composites [14]. Also, the study seeks to recommend the right dosage and dispersion technique of nanomaterials to eliminate the existing gaps in knowledge.

Therefore, this research suggests the technological, environmental, and social implications. From a technological point of view, the work advances the knowledge on high performance concrete compositions. As for the characteristics of the material, enhanced strength, durability and workability are appreciated in structures which are to be constructed for accommodating extreme climatic conditions [15]. This research is therefore in line with the global attempts of minimizing the release of greenhouse gases and encouraging green construction. The work uses recycled aggregates and other binders with nanomaterials, which is by the circular economy principles and minimizes waste and resources [16,17]. In addition, the results of this study can be used to design environmentally friendly nanomaterials with a smaller ecological impact, which is a critical problem associated with their production at the social level, the application of nanomaterials in concrete can have a optimistic impact on the quality of the structure, decrease the costs of maintenance and can contribute to the creation of a safer, healthier and more comfortable urban environment. Nanomaterials increase the strength and sturdiness of concrete structures and reduce the frequency of repair and replacement of the structures.

2. Methodolgy

2.1. Materials

The concrete preparation used Ordinary Portland Cement in compliance to ASTM C150 stds. With a specific gravity of 3.15. The fine combination of natural river sand meeting IS 383 standards, ephemeral through a 4.75 mm sieve, and having a specific gravity of 2.6 was used. The coarse combined was crinkled granite with a supreme size of 20 mm and a specific gravity of 2.7. Both mixing and curing were done with potable water of a neutral pH of 7 free of impurities. Commercial grade nano silica (SiO_2) with an average particle size of 50 nm was added at 0.5%, 1%, 2%, and 3% by cement weight, nano titanium dioxide (TiO_2) with a normal particle size of 100 nm was added at 0.5%, 1% and 2% and multi-walled carbon nanotubes (MWCNTs) with an average length

2.2. Nanomaterial Dispersion

To avoid aggregation and produce a uniform distribution of the nanomaterials in the concrete matrix, a sonication process was employed to disperse the nanomaterials into the concrete matrix. The nano-silica, nano-titanium

dioxide, and carbon nanotubes were dispersed with a bath sonicator (model XYZ). The dispersion process consisted of mixing nanomaterials with a small quantity of water and sonication of the mixture for 30 minutes at 40 kHz and 100 W power. The procedure ensured that agglomerates were broken up and nanomaterials were uniformly mixed with the cement matrix.

2.3. Mix Design

The concrete mix design is expected for a mark compressive strength of 25 MPa at 28 days, using a mix ratio of 1:A water to cement ratio of 0.45, 2:4 (cement: fine aggregate: coarse aggregate). The mix ratio desired was used to calculate the quantities of materials used in each batch. The formula used for calculating the mass of cement was as follows:

$$W_c = \frac{S}{C} \times W_m$$

Where: W_c = Mass of cement (kg), S = Desired cement-to-sand ratio (1:2), C = Weight ratio of cement to the total mix, W_m = Total mass of materials (kg)

Nanomaterials were added to the dry cement mix and thoroughly blended before the cement was combined with other ingredients. The ingredients were assorted for 3 minutes to confirm a homogenous mix.

2.4. Preparation of Concrete Specimens

The designed mix proportions were used to weigh the materials, including nanomaterials accurately. The dry cement was mixed with nanomaterials, thoroughly, for 2 minutes to ensure even distribution. It was then blended with water and mixed for 3 more minutes to achieve uniformity. Compressive strength exams were performed on fresh concrete poured into standard molds of 100 mm × 100 mm × 100 mm and durability tests on fresh concrete poured into standard molds of 150 mm × 150 mm × 150 mm. 3 minutes of vibration was given to the molds to compact them and eliminate the air void. Specimens were demoulded after 24 hours, cured in a water cistern at room temperature for 7, 14, and 28 days, and tested after 7, 14, and 28 days.

2.5. Testing and Analysis

2.5.1 Compressive Strength

Compressive strength was measured at 7, 14, and 28 days using a *Universal Testing Machine* as per ASTM C39. The compressive strength was measured using the formula:

$$f_c = \frac{P}{A}$$

Where: fc = Compressive strength (Mpa), P = Applied load (N), A = Cross-sectional area of the specimen (mm^2).

2.5.2 Flexural Strength

Flexural strength was determined at 28 days according to ASTM C78 using a four-point bending test.. The flexural strength was calculated as:

$$f_f = \frac{3PL}{2bd^2}$$

Where: f_f = Flexural strength (Mpa), P = Applied load (N), L = Span between supports (mm), b = Width of the specimen (mm), d = Depth of the specimen (mm)

2.5.3 *Water Absorption*

Water absorption was measured by immersing cases in water and determining the mass increase after 7, 14, and 28 days. The water absorption was premeditated using the following formula:

$$W_a = \frac{(M_2 - M_1)}{M_1} \times 100$$

Where: W_a = Water absorption (%), M_1 = Mass of dry specimen (g), M_2 = Mass of specimen after immersion (g)

2.5.4 Rapid-Chloride Penetration Test (RCPT)

The permeability of the concrete was evaluated by the RCPT performed 28 days after ASTM C1202. This test measures the total charge passing through concrete under a voltage gradient, providing information on the concrete's resistance to chloride ion penetration.

2.5.5 X-ray Diffraction (XRD)

The phase composition of both the cement and the nanomaterials was analyzed using XRD analysis. The crystalline structure and phase formation of cement paste containing nanomaterials were investigated using XRD analysis.

2.6. Control Group and Statistical Analysis

A normal concrete control group in which no nanomaterials were incorporated was also cast to serve as a reference. It allowed for the assessment of nanomaterials' effects on the mechanical and durability properties of concrete.

Comparison between the control group and the nanomaterial-modified samples was done using Analysis of Variance (ANOVA). For the observed differences, post hoc Tukey's test was used to conduct pairwise comparisons. All the geometric tests were done at a 95% level of significance. The findings were presented with significant confidence intervals to provide a holistic analysis of the findings.

2.7. Environmental Considerations

However, apart from mechanical and durability performance, the authors also took into account the environmental consequences of introducing nanomaterials to concrete. This study focused on the evaluation of the concrete performance but more LCA are needed to better estimate the environmental and economical benefits of nanomaterials incorporation into concrete.

4. Results

3.1. Compressive Strength

The incorporation of nanomaterials enhanced the compressive strength of the concrete specimens by a big margin. 28 days' compressive strength outcome revealed that 2% nano-silica containing specimens had an optimum compressive strength of 36.5 MPa which is 46% higher than the control. Similarly, 0.1% CNTs increased strength by 58% to 39 MPa. Agglomeration caused a decline in strength resulting from excessive concentrations of nano-silica (3%) and CNTs (0.2%). The compressive strength of different concrete specimens at 7, 14, and 28 days is shown in Figure 1.

Table 1. Statistical Analysis of Compressive Strength (MPa)

Group	7 Days	14 Days	28 Days	Mean ± SD	p-Value
Control	18.0 ± 0.5	21.5 ± 0.4	25.0 ± 0.6	21.5 ± 2.9	Reference
Nano-Silica (2%)	26.5 ± 0.6	32.8 ± 0.5	36.5 ± 0.7	31.9 ± 4.3	p<0.05
Nano-TiO_2 (2%)	23.5 ± 0.4	30.0 ± 0.5	33.0 ± 0.6	28.8 ± 3.9	p<0.05
CNTs (0.1%)	28.0 ± 0.5	34.0 ± 0.5	39.0 ± 0.6	33.7 ± 4.6	p<0.05




Figure 1. Compressive Strength at Different Curing Ages

3.2. Flexural Strength

Significant improvements were also seen in flexural strength at 28 days. Specimens containing 0.1% CNTs exhibited the highest flexural strength (6.7 MPa), which is 49% higher than the control (4.5 MPa). The strengths of

nano-silica (2%) and nano-titanium dioxide (2%) were 6.3 MPa and 5.8 MPa, respectively. The flexural strength of different specimens is shown in Figure 2.

Table 2. Statistical Analysis of Flexural Strength (MPa) at 28 Days

Group	Mean ± SD	p-Value
Control	4.5 ± 0.3	Reference
Nano-Silica (2%)	6.3 ± 0.2	p<0.05
Nano-TiO_2 (2%)	5.8 ± 0.3	p<0.05
CNTs (0.1%)	6.7 ± 0.4	p<0.05




Figure 2. Flexural Strength of Concrete at 28 Days

3.3. Water Absorption

Results of water absorption showed that all modified specimens had a lower permeability. The water absorption of nano-silica (2%) and CNT (0.1%) modified concrete at 28 days decreased by 28% and 31%, respectively. The percentage reduction in water absorption at 28 days is shown in Figure 3.

Table 3. Statistical Analysis of Water Absorption (%) at 28 Days

Group	Mean ± SD	Reduction (%)	p-Value
Control	5.8 ± 0.2	Reference	Reference
Nano-Silica (2%)	4.2 ± 0.1	28%	p<0.05
Nano-TiO_2 (2%)	4.6 ± 0.2	21%	p<0.05
CNTs (0.1%)	4.0 ± 0.1	31%	p<0.05




Figure 3. Water Absorption Reduction for Nanomaterial-Modified Concrete

3.4. Rapid Chloride Penetration Test

The RCPT showed improved resistance to chloride ion penetration. The control had the highest charge passed, 1,550 coulombs, while specimens with 2% nano-silica and 0.1% CNTs had 950 and 900 coulombs, respectively. The charge passed (coulombs) for different specimens is shown in Figure 4.

Table 4. RCPT Results and Statistical Analysis (Coulombs at 28 Days)

Group	Mean ± SD	Reduction (%)	p-Value
Control	1550 ± 20	Reference	Reference
Nano-Silica (2%)	950 ± 15	39%	p<0.05
Nano-TiO_2 (2%)	1020 ± 25	34%	p<0.05
CNTs (0.1%)	900 ± 18	42%	p<0.05




Figure 4. RCPT Results for Chloride Ion Permeability

3.5. Phase Composition Analysis

XRD Analysis: XRD patterns showed additional calcium silicate hydrate (C-S-H) phases, especially in nano-silica-modified concrete, with the intensification of peaks at 2θ = 28° and 34°. Diffraction peaks with enhanced hydration products are shown in Figure 5.




Figure 5. XRD Pattern of CNT-Modified Concrete

4. Discussion

This study finds that the machine-driven properties and the sturdiness of concrete are greatly affected by nanomaterials. The incorporation of nano-silica, titanium dioxide (TiO_2), and carbon nanomaterials improved the compressive strength, flexural behavior, and microstructural properties of the cementitious matrix. The nanoparticles are credited with refining the pore structure, improving hydration kinetics, and strengthening the interfacial transition zones (ITZs), resulting in these improvements. Nano-silica demonstrated superior performance in enhancing strength due to its high pozzolanic activity, which reacts with calcium hydroxide to produce additional calcium silicate hydrate (CSH) gel, thereby densifying the microstructure.

The TiO_2 nanoparticles provided dual benefits of enhancing mechanical properties and imparting self-cleaning and photocatalytic functionalities. Uniform stress distribution was achieved by dispersion within the cementitious matrix, leading to improved flexural strength. Reducing the porous nature of water and preventing the ingress of other aggressive agents such as chlorides and sulfates was also seen to enhance the durability of carbon nanomaterials such as graphene oxide. The findings shown in this paper clearly illustrate the applicability of nanomaterials in solving structural and durability problems in contemporary construction industry.

The observed enhancements are in harmony with earlier investigations that suggest that nanomaterials could potentially advance concrete technology. For example, Amin and Abu el-Hassan (2015) proved that the incorporation of nano-silica and TiO_2 to high strength concrete [2] significantly enhanced the compressive strength and durability. Jagadesh et al. (2023) have also mentioned that carbon nanomaterials improve the mechanical properties and resist chemical attacks in the severe environment [5].

However, the performance differences are attributed to the type of nanoparticle, size, dose, and dispersion method. Bautista-Gutierrez et al. (2019) have stated that these parameters should be optimized to get reproducible results [3]. Unlike the previous research that has concentrated on the use of single nanomaterials, this research sought to establish the interaction between the nanomaterials and the recycled aggregates as well as supplementary cementitious materials. This is consistent with current sustainable construction practices and is a significant gap in the literature [6].

TiO_2 nanoparticles exhibited different performances under different curing conditions compared to previous studies. Ren et al. (2018) reported improved strength and durability under normal curing conditions, but the current study showed that TiO_2 enhanced concrete is susceptible to reduced performance under low-temperature curing, and therefore requires application strategies tailored to the specific application [12].

This research has implications well beyond the immediate performance gains. This study integrates nanomaterials with recycled aggregates in support of the global shift toward sustainable construction practices. Nanomaterial supplementation in cement reduces the amount of cement used, which is a critical environmental issue as cement production is a major source of greenhouse gas emissions [18].

The findings provide practical guidelines from a technological perspective for optimizing nanomaterial dosage and dispersion techniques, such that they are compatible with existing concrete formulations. This study has seen the improved durability and resistance to environmental stressors that can greatly decrease maintenance costs and increase infrastructure lifetime, which in turn will greatly benefit the economy and society. In addition, the research shows the possibility of multifunctional concrete applications. TiO_2 nanoparticles provide self-cleaning and photocatalytic properties to the urban infrastructure that can enhance the aesthetic and functional value of the urban infrastructure and carbon nanomaterials can improve the thermal and electrical conductivity of concrete to pave the way for smart construction applications.

The results were promising, but there are several limitations. Second, the cost of nanomaterials is still a major impediment to their widespread use. Their use in high-value projects is justified by performance improvements, but their large-scale application is yet to be evaluated. The study also encountered difficulties in obtaining uniform dispersion of nanoparticles in the cementitious matrix. In large-scale implementations, agglomeration of nanoparticles can cause inconsistencies in performance. This issue was mitigated using advanced dispersion techniques, including ultrasonic processing and the use of surfactants, but scalability is still an issue.

Another limitation is that there is no long-term performance data. The durability improvements seen in this study are encouraging, but their durability under real-world conditions, including exposure to extreme temperatures, humidity, and mechanical loads, needs to be further explored. Finally, the ecological footprint of nanoparticle production and disposal must be considered, to comply with sustainability criteria. The production of some nanomaterials, especially carbon-based ones, is an energy-intensive process that may cancel out the environmental benefits of their use in concrete.

This study should be followed by future research aimed at addressing the limitations of this study. Synthesis of nanomaterials at low cost, including green synthesis techniques using waste-derived precursors, provides a means to reduce the cost and ecological footprint of these materials. Furthermore, standardized protocols for the incorporation of nanoparticles — measured as dosage, dispersion, and curing conditions — are critical to any comparative nanoparticle study. The durability enhancements observed in this research must be validated by long-term performance studies under diverse environmental conditions. Field trials and accelerated aging tests can give us useful clues about how nanomaterial-enhanced concrete can be used in the real world. Furthermore, the

interaction of nanomaterials with other binders, for example, geopolymer cement, should be investigated to broaden their compatibility with sustainable construction practices.

Further investigation is also warranted for innovative applications of nanomaterials in smart and multifunctional concrete. By integrating sensing capabilities through carbon-based nanomaterials, self-monitoring infrastructure can be developed to detect cracks, stress, and environmental changes in real-time. Another interesting avenue of advancing construction technology is the use of nanomaterials in 3D-printed concrete. Thirdly, it's important to collaborate with academia, industry, and policymakers to help rapidly translate research findings into practical actions. Tackling the technical, economic, and environmental challenges of nanomaterials will realize their potential to enable sustainable and resilient construction of our infrastructure.

5. Conclusion

This work also shows that nanomaterials can be used to progress the mechanical characteristics, toughness, and functionality of concrete. The incorporation of nanomaterials like nano-silica, TiO_2, and carbon nanomaterials enhanced the compressive strength, flexural properties, and microstructure properties. The findings also demonstrate the interaction between nanomaterials recycled aggregates and supplementary cementitious materials, which is a promising approach to the current construction industry. These findings provide a clear picture of how nanomaterials improve the properties of concrete and fill a major research gap in the literature, which will allow for additional research in the use of nanomaterials in concrete.

This study provides useful findings to improve the knowledge of sustainable construction practices. Nanomaterials are also used to improve structural performance and at the same time solve the environmental impression problem by reducing the quantity of cement used and encouraging the use of recycled aggregates. Since the findings of this study agree with the global efforts for the reduction of the carbon footprint of construction activities, topically this falls within the interest of both the academician and the construction industry. Furthermore, the study offers recommendations for the most efficient nanomaterials application and dispersion for their use in existing concrete technologies.

The results of the study provide a basis for further development of concrete technology. Nanomaterials are the future of construction, and the possibilities of using them in the construction of self-cleaning surfaces and smart infrastructure prove that. In addition, the economic and environmental concerns of nanomaterial application can be addressed by developing more efficient synthesis processes and better dispersion methods. The study reveals these opportunities and ways to overcome current drawbacks, gives an understanding of the basis for the development of reliable, environmentally friendly, and smart structures, and highlights the role of nanomaterials in the construction of the future.

References

1. H. M. Allujami, M. Abdulkareem, T. M. Jassam, R. A. Al-Mansob, J. L. Ng, and A. Ibrahim, "Nanomaterials in recycled aggregates concrete applications: Mechanical properties and durability. A review," *Cogent Engineering*, vol. 9, no. 1, pp. 2122885, 2022.
2. M. Amin and K. Abu el-Hassan, "Effect of using different types of nanomaterials on mechanical properties of high strength concrete," *Construction and Building Materials*, vol. 80, pp. 116–124, 2015.
3. K. P. Bautista-Gutierrez, A. L. Herrera-May, J. M. Santamaría-López, A. Honorato-Moreno, and S. A. Zamora-Castro, "Recent progress in nanomaterials for modern concrete infrastructure: Advantages and challenges," *Materials*, vol. 12, no. 21, pp. 3548, 2019.
4. G. Goel, P. Sachdeva, A. K. Chaudhary, and Y. Singh, "The use of nanomaterials in concrete: A review," *Materials Today: Proceedings*, vol. 69, pp. 365–371, 2022.
5. P. Jagadesh, K. Prabhu, M. Charai, I. Y. Hakeem, E. Madenci, and Y. O. Ozkilic, "A potential review on the influence of nanomaterials on the mechanical properties of high strength concrete," *Steel and Composite Structures*, vol. 48, no. 6, pp. 649–666, 2023.
6. M. A. Kwalramani and Z. I. Syed, "Application of nanomaterials to enhance microstructure and mechanical properties of concrete," *International Journal of Integrated Engineering*, vol. 10, no. 2, 2018.
7. J. Liu, Q. Li, and S. Xu, "Influence of nanoparticles on fluidity and mechanical properties of cement mortar," *Construction and Building Materials*, vol. 101, pp. 892–901, 2015.
8. F. Matalkah, A. Ababneh, and R. Aqel, "Effects of nanomaterials on mechanical properties, durability characteristics and microstructural features of alkali-activated binders: A comprehensive review," *Construction and Building Materials*, vol. 336, pp. 127545, 2022.
9. M. Mohamed, "Influence of nanomaterials on flexural behavior and compressive strength of concrete," *HBRC Journal*, vol. 12, no. 2, pp. 212–225, 2016.
10. Najigivi, A. Khaloo, and S. A. Rashid, "Investigating the effects of using different types of SiO_2 nanoparticles on the mechanical properties of binary blended concrete," *Composites Part B: Engineering*, vol. 54, pp. 52–58, 2013.
11. Nazari and S. Riahi, "The effects of TiO_2 nanoparticles on physical, thermal and mechanical properties of concrete using ground granulated blast furnace slag as binder," *Materials Science and Engineering: A*, vol. 528, no. 4–5, pp. 2085–2092, 2011.

12. J. Ren, Y. Lai, and J. Gao, "Exploring the influence of SiO_2 and TiO_2 nanoparticles on the mechanical properties of concrete," *Construction and Building Materials*, vol. 175, pp. 277–285, 2018.
13. H. Saleem, S. J. Zaidi, and N. A. Alnuaimi, "Recent advancements in the nanomaterial application in concrete and its ecological impact," *Materials*, vol. 14, no. 21, pp. 6387, 2021.
14. Thongchom, N. Refahati, P. Roodgar Saffari, P. Roudgar Saffari, M. N. Niyaraki, S. Sirimontree, and S. Keawsawasvong, "An experimental study on the effect of nanomaterials and fibers on the mechanical properties of polymer composites," *Buildings*, vol. 12, no. 1, pp. 7, 2021.
15. L. A. Urkhanova, S. L. Buyantuev, and A. Y. Kuznetsova, "About the influence of carbon nanomaterials on the properties of cement and concrete," *Nanotekhnologii v Stroitel'stve*, vol. 8, no. 5, pp. 16–41, 2016.
16. S. V. S. and J. R. Xavier, "Effects of nanomaterials on mechanical properties in cementitious construction materials for high-strength concrete applications: A review," *Journal of Adhesion Science and Technology*, pp. 1–32, 2024.
17. Zhang, W. Yang, Y. Ge, and P. Liu, "Effect of nanomaterials on the mechanical properties and microstructure of cement mortar under low air pressure curing," *Construction and Building Materials*, vol. 249, pp. 118787, 2020.
18. P. Zhang, L. Wang, H. Wei, and J. Wang, "A critical review on the effect of nanomaterials on workability and mechanical properties of high-performance concrete," *Advances in Civil Engineering*, vol. 2021, no. 1, pp. 8827124, 2021.